

FEATURES	<p>EXTRACOTE Emulsion Paint for wall interior and ceiling. Available in matt finish.</p> <p>Provides good hiding power to conceal wall imperfection and easy to apply.</p> <p>It is suitable for the decoration and protection of all interior building surfaces.</p> <p>Typical Use ; It is ideal for application ceiling and interior concretes, new and old masonry surfaces, plasters, bricks, asbestos shingled and siding.</p>																																										
TECHNICAL INFORMATION	<table border="0"> <tr> <td>Type</td> <td colspan="2">Emulsion paint</td> </tr> <tr> <td>Color</td> <td colspan="2">Wide range of colors. Please refer to colour card.</td> </tr> <tr> <td>Film appearance</td> <td colspan="2">Matt</td> </tr> <tr> <td>Specific gravity</td> <td colspan="2">1.39-1.51</td> </tr> <tr> <td>Solid by volume</td> <td>33 - 37</td> <td>% ,other colours will vary.</td> </tr> <tr> <td>Solid by weight</td> <td>52 - 58</td> <td>%</td> </tr> <tr> <td>Flash point</td> <td>N/A</td> <td>°C</td> </tr> <tr> <td>Volatile organic compounds (VOCs)</td> <td>-</td> <td>gram / litre</td> </tr> <tr> <td>Wet film thickness</td> <td>90-110</td> <td>microns</td> </tr> <tr> <td>Dry film thickness</td> <td>35-40</td> <td>microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>8 -10</td> <td>sq.meter / Kg / coat</td> </tr> </table> <p>Remark – Actual surface coverage will depend on surface irregularities, mixing, application condition, method and technique; as well as the structure and dimensions of the object to be coated.</p> <table border="0"> <tr> <td>Touch dry (25-30 °C)</td> <td>30</td> <td>minutes</td> </tr> <tr> <td>Recoat dry (25-30 °C)</td> <td>2</td> <td>hours</td> </tr> <tr> <td>Full cure (25-30 °C)</td> <td>7</td> <td>days</td> </tr> </table>	Type	Emulsion paint		Color	Wide range of colors. Please refer to colour card.		Film appearance	Matt		Specific gravity	1.39-1.51		Solid by volume	33 - 37	% ,other colours will vary.	Solid by weight	52 - 58	%	Flash point	N/A	°C	Volatile organic compounds (VOCs)	-	gram / litre	Wet film thickness	90-110	microns	Dry film thickness	35-40	microns	Theoretical coverage	8 -10	sq.meter / Kg / coat	Touch dry (25-30 °C)	30	minutes	Recoat dry (25-30 °C)	2	hours	Full cure (25-30 °C)	7	days
Type	Emulsion paint																																										
Color	Wide range of colors. Please refer to colour card.																																										
Film appearance	Matt																																										
Specific gravity	1.39-1.51																																										
Solid by volume	33 - 37	% ,other colours will vary.																																									
Solid by weight	52 - 58	%																																									
Flash point	N/A	°C																																									
Volatile organic compounds (VOCs)	-	gram / litre																																									
Wet film thickness	90-110	microns																																									
Dry film thickness	35-40	microns																																									
Theoretical coverage	8 -10	sq.meter / Kg / coat																																									
Touch dry (25-30 °C)	30	minutes																																									
Recoat dry (25-30 °C)	2	hours																																									
Full cure (25-30 °C)	7	days																																									
REFERENCE STANDARD																																											
APPLICATION	<table border="0"> <tr> <td>Tools</td> <td colspan="2">Roller, Brush, Spray</td> </tr> <tr> <td>Diluent</td> <td colspan="2">Clean Water</td> </tr> <tr> <td rowspan="2">Dilution</td> <td>15-20</td> <td>% (roller and brush)</td> </tr> <tr> <td>20-25</td> <td>% (spray)</td> </tr> </table>	Tools	Roller, Brush, Spray		Diluent	Clean Water		Dilution	15-20	% (roller and brush)	20-25	% (spray)																															
Tools	Roller, Brush, Spray																																										
Diluent	Clean Water																																										
Dilution	15-20	% (roller and brush)																																									
	20-25	% (spray)																																									
APPLICATION SYSTEM	<table border="0"> <tr> <td>Surface Preparation</td> <td rowspan="2">Powdery and chalky surface must be scrubbed and cleaned with water Fungus and mildew growth must be cleaned off. Left to dry for 2-3 days. For more smooth surface use TOA Acrylic Wall Putty.</td> </tr> <tr> <td>Old surface</td> </tr> <tr> <td>New surface</td> <td>Substrate must be completely cured and dried (~ 1 month) free from oil ,grease ,mildew, from release agents and foreign matters. For more smooth surface use TOA Acrylic Wall Putty</td> </tr> <tr> <td>Coating system</td> <td></td> </tr> <tr> <td>Primer For Old Surface</td> <td>Apply 1-2 coats of TOA PRIMER</td> </tr> </table>	Surface Preparation	Powdery and chalky surface must be scrubbed and cleaned with water Fungus and mildew growth must be cleaned off. Left to dry for 2-3 days. For more smooth surface use TOA Acrylic Wall Putty.	Old surface	New surface	Substrate must be completely cured and dried (~ 1 month) free from oil ,grease ,mildew, from release agents and foreign matters. For more smooth surface use TOA Acrylic Wall Putty	Coating system		Primer For Old Surface	Apply 1-2 coats of TOA PRIMER																																	
Surface Preparation	Powdery and chalky surface must be scrubbed and cleaned with water Fungus and mildew growth must be cleaned off. Left to dry for 2-3 days. For more smooth surface use TOA Acrylic Wall Putty.																																										
Old surface																																											
New surface	Substrate must be completely cured and dried (~ 1 month) free from oil ,grease ,mildew, from release agents and foreign matters. For more smooth surface use TOA Acrylic Wall Putty																																										
Coating system																																											
Primer For Old Surface	Apply 1-2 coats of TOA PRIMER																																										

Primer For New Surface Topcoat	Apply 1-2 coats of TOA 4 SEASONS PRIMER Apply 2-3 coats of EXTRACOTE
HANDLING AND STORAGE Storage condition Shelf life	The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed. 5 years from producing at 25-35 °C
HEALTH AND SAFETY	Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.